-2-

## Amendments to the Claims:

ID:3M 220-11-01

This listing of claims will replace all prior versions and listings of claims in the application.

## **Listing of Claims:**

- 1 18 (canceled)
- 19. (withdrawn) A method of applying a pressure sensitive adhesive to a substrate; the method comprising:

providing a substrate;

applying a latent, over-tackified, adhesive to the substrate; and applying a liquid plasticizing agent to activate the latent, over-tackified, adhesive to form a pressure sensitive adhesive.

- (withdrawn) The method of claim 19 wherein applying the plasticizing agent 20. occurs subsequent to applying the latent, over-tackified, adhesive.
- (withdrawn) The method of claim 20 wherein the plasticizing agent is applied in 21. selective regions to the latent, over-tackified, adhesive disposed on the substrate.
- (withdrawn) The method of claim 19 wherein the latent, over-tackified, 22. adhesive and the plasticizing agent are simultaneously applied to the substrate.
- (withdrawn) The method of claim 19 wherein the plasticizing agent is non-23. volatile.
- (withdrawn) The method of claim 19 wherein the plasticizing agent is non-24. reactive.
- (withdrawn) The method of claim 19 wherein the latent, over-tackified, pressure 25. sensitive adhesive comprises a natural rubber, synthetic rubber, styrene block copolymer, (meth)acrylic polymer, poly(alpha-olefin), or silicone.

Δ

ID:3M 220-11-01

-3-

 (withdrawn) A method of adhering substrates together; the method comprising: providing a first substrate;

applying a latent, over-tackified, adhesive to the first substrate; and applying a liquid plasticizing agent to activate the latent, over-tackified, adhesive to form a pressure sensitive adhesive; and

applying a second substrate to contact the pressure sensitive adhesive disposed on the first substrate.

- 27. (withdrawn) The method of claim 26 wherein applying the plasticizing agent occurs subsequent to applying the latent, over-tackified, adhesive.
- 28. (withdrawn) The method of claim 27 wherein the plasticizing agent is applied in selective regions to the latent, over-tackified, adhesive disposed on the substrate.
- 29. (withdrawn) The method of claim 26 wherein the plasticizing agent is non-volatile.
- 30. (withdrawn) The method of claim 26 wherein the plasticizing agent is non-reactive.
- 31. (withdrawn) The method of claim 26 wherein the latent, over-tackified, pressure sensitive adhesive comprises a natural rubber, synthetic rubber, styrene block copolymer, (meth)acrylic polymer, poly(alpha-olefin), or silicone.
- 32. (withdrawn) An adhesive article prepared by the method of claim 19.
- 33. (withdrawn) The adhesive article of claim 32 which is in the form of a tape.
- 34. (currently amended) A method of applying a pressure sensitive adhesive to a substrate; the method comprising:

providing a substrate;

applying a latent, over-tackified, adhesive and a solid plasticizing agent simultaneously to a substrate; and

applying heat to activate the latent, over-tackified, adhesive to form a pressure sensitive adhesive;

5

-4-

wherein the latent, over-tackified, adhesive is selected from the group consisting of (meth)acrylic polymer, poly(alpha-olefin), and silicone.

- 35. (currently amended) The method of claim 34 wherein the plasticizing agent is applied in selective regions to the latent; over tackified, adhesive disposed on the substrate.
- 36. (currently amended) The method of claim 35 34 wherein heat is applied in selective regions to the plasticizing agent and latent, over-tackified, adhesive disposed on the substrate.
- 37. (previously presented) The method of claim 34 wherein the plasticizing agent is non-reactive.
- 38. (canceled)
- 39. (currently amended) A method of adhering substrates together; the method comprising:

providing a first substrate;

applying a latent, over-tackified, adhesive and a solid plasticizing agent simultaneously to a substrate;

applying heat to activate the latent, over-tackified, adhesive to form a pressure sensitive adhesive; and

applying a second substrate to contact the pressure sensitive adhesive disposed on the first substrate;

wherein the latent, over-tackified, adhesive is selected from the group consisting of (meth)acrylic polymer, poly(alpha-olefin), and silicone.

- 40. (Currently amended) The method of claim 39 wherein the plasticizing agent is applied in selective regions to the latent, over-tackified, adhesive disposed on the substrate.
- 41. (previously presented) The method of claim 39 wherein the plasticizing agent is non-reactive.

-5-

- 42. (canceled)
- 43. (previously presented) An adhesive article prepared by the method of claim 34.
- 44. (previously presented) The adhesive article of claim 43 which is in the form of a tape.